

539,051

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
1 July 2004 (01.07.2004)

PCT

(10) International Publication Number
WO 2004/055261 A1

(51) International Patent Classification⁷: **D06M 16/00**

(21) International Application Number:
PCT/FI2003/000964

(22) International Filing Date:
16 December 2003 (16.12.2003)

(25) Filing Language: Finnish

(26) Publication Language: English

(30) Priority Data:
20022204 16 December 2002 (16.12.2002) FI

(71) Applicant (*for all designated States except US*): **MELO-COTON OY** [FI/FI]; Yrittäjänkatu 22, FIN-50130 Mikkeli (FI).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): **MERIKOSKI, Pia** [FI/FI]; Liinasaarentie 3, FIN-02160 Espoo (FI).

(74) Agent: **SEPPO LAINE OY**; Itämerenkatu 3 B, FIN-00180 Helsinki (FI).

(81) Designated States (*national*): AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, EG, ES, FI (utility model), FI, GB,

GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK (utility model), SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO utility model (BW), ARIPO patent (BW), ARIPO utility model (GH), ARIPO patent (GH), ARIPO utility model (GM), ARIPO patent (GM), ARIPO utility model (KE), ARIPO patent (KE), ARIPO utility model (LS), ARIPO patent (LS), ARIPO utility model (MW), ARIPO patent (MW), ARIPO utility model (MZ), ARIPO patent (MZ), ARIPO utility model (SD), ARIPO patent (SD), ARIPO utility model (SL), ARIPO patent (SL), ARIPO utility model (SZ), ARIPO patent (SZ), ARIPO utility model (TZ), ARIPO patent (TZ), ARIPO utility model (UG), ARIPO patent (UG), ARIPO utility model (ZM), ARIPO patent (ZM), ARIPO utility model (ZW), ARIPO patent (ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **PROCESS FOR BIOTECHNICAL FINISHING OF WOOL**

(57) Abstract: The present invention relates to a method for finishing woollen textiles. According to the method, the woollen textile in an aqueous solution is brought into contact with protease enzyme in a large amount of water so that the woollen textile is moved as little as possible or not at all, at a temperature of about 60°C or less for 10 to 90 min. The enzyme is inactivated and the woollen textile is taken to dry in mechanical drying at a temperature of about 60°C or less to reach residual moisture content of 10 to 45 %, and the final drying is carried out without mechanics.

WO 2004/055261 A1